<u>Claims</u>:

1	Process for the manufacture of optical fibers comprising:	
2	(a) preparing an optical fiber preform,	
3	(b) heating the preform to the softening temperature, and	
4	(c) drawing an optical fiber from the preform	
5	the invention characterized in that the optical fiber preform is produced by:	
6	(i) preparing a porous silica body of silica particles,	
7	(ii) heating the porous silica body in a fluorine atmosphere for a	
8	period of 10 - 240 minutes to predeposit fluorine on the silica	
9	particles, and	
10	(iii) heating the porous silica body at a temperature greater than	
11	1300 °C, in an atmosphere devoid of fluorine, to consolidate the	
12	porous silica body into a preform.	
1	2. The process of claim 1 wherein the fluorine atmosphere comprises SiF ₄ .	
1	3. The process of claim 2 wherein the fluorine atmosphere is greater than 10%	
2	SiF ₄ .	
1	4. Process for the manufacture of optical fiber preforms comprising:	
2	(a) preparing a porous silica body of silica particles, said porous silica	
3	body having a weight greater than 5 kg.	

4	

8

9

10

1

- (b) heating the porous silica body to a temperature in the range

 800-1000 ^OC in a fluorine atmosphere for a period of 10 240 minutes to

 predeposit fluorine on the silica particles, and
 - (c) heating the porous silica body at a temperature greater than 1300 $^{\circ}$ C, in an atmosphere devoid of fluorine, to consolidate the porous silica body.
 - 5. The process of claim 4 wherein the fluorine atmosphere comprises SiF₄.